

Product Code:

546-8003 PLASTISEAL LOW VOC

VISCOSITY:	17-18 sec Zahn #2 at 25°C
FLASH POINT:	-15°C
DENSITY (kg/l):	0.91 ± 2% at 25°C
SOLID (% by weight):	22± 2%
SOLID (% by volume):	14 ± 2%
SHELF LIFE (months):	12

Product Description:

Low-voc, hybrid pre-catalyzed sealer (vinyl/nitrocellulose). Easy sanding and fast drying time.

Uses:

Used as a protective coatings for wood. For interior uses only.

Environmental Data (as supplied):

VOC less exempt lb/gal:	5.72
VOC lb/gal:	4.43
VOC less exempt g/l:	686
VOC g/l:	531
VOC lb/lb Solid:	2.69
VHAPs lb/lb Solid:	1.00

See individual compliance sheets for specific data

Application Data:

SUGGESTED USES: Spray
MIXING RATION: N/A
POT LIFE: N/A
APPLICATION VISCOSITY: 17-18 sec Zahn #2 at 25°C
REDUCER: N/A
RETARDER: N/A
CLEAN-UP SOLVENT: 803-1339
APPLIED FILM THICKNESS: 3 to 5 mils wet



AkzoNobel

Directions for Use

PLASTISEAL LOW VOC
546-8003

Surface Preparation:

Wood must be sanded with a #120, 150 or 180 grit paper and free of dust and all contaminants. Sealer must be sanded with a #280/320 paper and the topcoat must be applied within 8 hours after the sanding.

General information:

PLASTISEAL LOW-VOC is applied in 1 or 2 coats of 3 to 5 mils. A thorough sanding of each coat is essential for proper adhesion. Eliminate all contact with metallic surfaces. Maximum film build of the topcoat should not exceed 1.5 mils dry. Maximum film build of the system should not exceed 4 mils dry.

To obtain complete cure, PLASTISEAL LOW-VOC should be applied at a temperature above 18°C and relative humidity below 65%. When drying, this product is not to be exposed to ammonia vapours. Finished surfaces must not be cleaned with ammonia containing products. Always use plastic or stainless equipment to eliminate discoloration due to oxidation.

PLASTISEAL LOW-VOC is use with topcoat 431-30XX, 431-71XX, 480-1XXX, 480-2XXX, 484-XXXX

THE CUSTOMER IS RESPONSIBLE FOR FOLLOWING THE RECOMMENDED APPLICATION PROCEDURES. FAILURE TO ADHERE TO THE RECOMMENDATIONS GIVEN INTHIS DATA SHEET WILL LIKELY RESULT IN UNSATISFACTORY FILM APPEARANCE OR FILM FAILURE. THE COMPLETE COATING SYSTEM SHOULD BE CHECKED FOR REQUIRED PROPERTIES PRIOR TO THE START-UP OF PRODUCTION.

Drying Times:

	At 68°F (Minimum Required)	At 122°F (Minimum Required)
Tack Free Time:	10-15 min	Flash off before entering oven
Dry to Sand:	30-45 min	30 min
Dry to Stack:	2 hours	1 hour

Note: Dry times are greatly affected by film build, porosity of substrate, air movement as well as heat and humidity. Temperatures are based on actual board temperature. This may vary depending on length of time for boards to reach these temperatures. Minimum curing temperatures of 64°F/18°C must be maintained throughout the curing cycle to achieve the film integrity as stated in product features.

These products are designed for industrial use only. AkzoNobel views safety as a top priority. Please refer to Material Safety Data Sheet for information on the safe use of this product.

Values shown are calculated estimates and should not be construed as product specifications. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and users assume all responsibility and liability for loss or damage arising from the use of our products whether used alone or a combination with other products. Use of unapproved or reclaimed solvent blends may reduce film properties and is not recommended.

Akzo Nobel Peintures Bois
274, St-Louis
Warwick, QC J0A 1M0
1-819-358-7500